



Akkreditiert gem.  
ISO/IEC 17025 (STS 411)

Procon Play & Leisure GmbH  
Van-der-Reis-Weg 11  
D 59590 Geseke

### Summary Test Results

IST Reference            7426/Kol  
  
Subject                    Testing of Surfaces for Playgrounds  
                              acc. EN 1177 „Impact attenuating playground surfacing “

Following, the test results are summarized which are reported in detail in our report no. 7426 dated March 6, 2009.

### Design of Surfaces Tested

Name		<b>SUREPLAY</b>
Description	40 - 100 mm	Playground Surfaces, poured-in-place two layer systems
Top Layer	10 mm	PU-bound EPDM-Granules, red-brown
Base Layer	30 - 90 mm	PU-bound Rubber fibers and granules

### Test Results

Surface	Thickness [mm]	Critical Drop Height [m]
SUREPLAY 40 mm	40	1.3
SUREPLAY 50 mm	50	1.5
SUREPLAY 70 mm	70	1.9
SUREPLAY 80 mm	80	2.4
SUREPLAY 100 mm	100	3.0

Eschenz, March 27, 2009

Dipl.-Ing. H.J. Kolitzus  
Director



Thomas Hartmann  
Lab Manager

